

Ridgewood

Rosewood

Pterocarpus Indicus

Technical Information

Density (kg/m ³ dry)	650	Durable
Specific Gravity	0.65	Sapwood Lyctid Susceptible
Modulus of Rupture (MPa dry)	95	Machining
Modulus of Elasticity (GPa dry)	12	Resistance to Split in Nailing
Radial Shrinkage %	1	Resistance to Split in Screwing
Tangential Shrinkage %	2	Gluing
Hardness (Janka) (kN)	5	Growing Region
Finish	Excellent	
Stability	Excellent	Availability

Description

Yes	Heartwood can be either golden brown or a dark blood red. Sapwood pale yellow.
No	Texture medium. Grain variable.
Excellent	The freshly cut wood has a fragrant odour often highly figured.
Good	<i>Also known as New Guinea Rosewood, Solomon Islands Rosewood.</i>
Good	Suitability
Good	<i>Boating</i>
Asia	<i>Cabinet Door</i>
Pacific	<i>Decking & Cladding</i>
Available	<i>Flooring & Staircase</i>
	<i>Furniture</i>
	<i>Joinery</i>