

Ridgewood

Jarrah Decking

Eucalyptus Marginata

Technical Information

Density (kg/m ³ dry)	820	Stability	Good
Specific Gravity	0.8	Sapwood Lyctid Susceptible	Yes
Modulus of Rupture (MPa dry)	112	Machining	Fair
Modulus of Elasticity (GPa dry)	13	Resistance to Split in Nailing	Fair
Radial Shrinkage %	5	Resistance to Split in Screwing	Fair
Tangential Shrinkage %	8	Gluing	Good
Hardness (Janka) (kN)	8.5	Growing Region	WA
Finish	Good	Availability	Widely

Description

The striking deep red to light pink colours of Jarrahas proven to be a popular choice for decking.

Jarrah is very hard-wearing and when treated with clear oil, its interlocking grain and vibrant colour add a touch of class to domestic decking and commercial applications.

A low-maintenance timber, Jarrah is versatile and can be used creatively in large or small areas to enhance landscaped areas and courtyards.

The classic, rich tone of Australian Jarrah is perfect where high-quality decking is required to complement thoughtful home and garden design.

Sizes

Pencil Round Four Corners
65mm×20mm
85mm×20mm
130mm×20mm

BAL

Bush-fire Attack Level 29
All AS 3959 Required Applications

