

Ridgewood

Jelutong

Dyera Costulata

Technical Information

Density (kg/m ³ dry)	400	Durable
Specific Gravity	0.46	Sapwood Lyctid Susceptible
Modulus of Rupture (MPa dry)	50	Machining
Modulus of Elasticity (GPa dry)	8	Resistance to Split in Nailing
Radial Shrinkage %	1	Resistance to Split in Screwing
Tangential Shrinkage %	2	Gluing
Hardness (Janka) (kN)	2	Growing Region
Finish	Excellent	
Stability	Excellent	Availability

Description

No	Heartwood is creamy white to straw coloured.
Yes	The grain is almost straight, the texture fine and even and of plain appearance.
Excellent	Jelutong is mainly used for pattern making.
Excellent	
Excellent	Suitability
Good	<i>Boating</i>
Asia	<i>Cabinet Door</i>
Pacific	<i>Joinery</i>
Available	