

Ridgewood

Accoya Radiata Pine

Technical Information

Density (kg/m ³ dry)	515	Durable	Yes
Specific Gravity	0.51	Sapwood Lyctid Susceptible	No
Modulus of Rupture (MPa dry)	90	Machining	Excellent
Modulus of Elasticity (GPa dry)	9	Resistance to Split in Nailing	Fair
Radial Shrinkage %	0.4	Resistance to Split in Screwing	Good
Tangential Shrinkage %	0.8	Gluing	Good
Hardness (Janka) (kN)	4.1	Growing Region	Europe
Finish	Excellent	Availability	Widely
Stability	Good		

Description

Accoya® is wood is chemical free modified timber using acetylation, which enables it to resist rot and defy the elements. Guaranteed for 50 years above ground and 25 years in ground. From joinery for the home to bridges submerged in water, Accoya® long life wood is a leading material that stands up to every application challenge.

Suitability
Decking & Cladding
Joinery
Boating
Furniture
Cabinetry

accoya 

