

Ridgewood

Karri *Eucalyptus Diversicolor*

Technical Information

Density (kg/m ³ dry)	900
Specific Gravity	0.88
Modulus of Rupture (MPa dry)	132
Modulus of Elasticity (GPa dry)	19
Radial Shrinkage %	4.5
Tangential Shrinkage %	10
Hardness (Janka) (kN)	9
Finish	Good

Stability	Good
Sapwood Lyctid Susceptible	No
Machining	Fair
Resistance to Split in Nailing	Fair
Resistance to Split in Screwing	Fair
Gluing	Fair
Growing Region	WA
Availability	Widely

Description

Heartwood is reddish brown, paler in colour than Jarrah when fresh, but maturing to a more uniform brown.

The grain is interlocked with some wavy grain, the texture is even and moderately coarse.

Suitability

Boating
Cabinet Door
Decking & Cladding
Flooring & Staircase
Furniture
Joinery

