

Ridgewood

Spotted Gum

Corymbia Maculata, Corymbia Citroedora, Eucalyptus Henryi

Technical Information

Density (kg/m ³ dry)	950	Durable	Yes
Specific Gravity	0.95	Sapwood Lyctid Susceptible	Yes
Modulus of Rupture (MPa dry)	150	Machining	Good
Modulus of Elasticity (GPa dry)	23	Resistance to Split in Nailing	Good
Radial Shrinkage %	4.5	Resistance to Split in Screwing	Good
Tangential Shrinkage %	6	Gluing	Poor
Hardness (Janka) (kN)	11	Growing Region	NSW & QLD
Finish	Good	Availability	Available
Stability	Fair		

Description

Heartwood pale to dark brown or chocolate. Sapwood is distinctively paler but there maybe a zone of intermediate wood.

Texture moderately coarse. Grain variable, the frequent presence of wavy grain produces an attractive fiddleback figure.

Slightly greasy nature. Gum veins common. Northern material is usually slightly denser, stronger and more durable than southern.

Also known as Lemon Scented Gum.

Suitability

Boating
Cabinet Door
Decking & Cladding
Flooring & Staircase
Furniture
Joinery

