

Ridgewood

Tasmanian Oak Flooring

Eucalyptus Obliqua

Technical Information

Density (kg/m ³ dry)	780	Stability	Good
Specific Gravity	0.78	Sapwood Lyctid Susceptible	Yes
Modulus of Rupture (MPa dry)	118	Machining	Good
Modulus of Elasticity (GPa dry)	15	Resistance to Split in Nailing	Good
Radial Shrinkage %	3.5	Resistance to Split in Screwing	Good
Tangential Shrinkage %	6.5	Gluing	Good
Hardness (Janka) (kN)	7	Growing Region	TAS
Finish	Good	Availability	Widely

Description

Tasmanian Oak flooring has a reputation in Australia and internationally as a durable, stable and attractive product. Tasmanian Oak is a warm, dense and resilient timber. As a flooring choice, Tasmanian Oak is without peer.

Harvested from the sustainably-managed and PEFC certified temperate forests of the north-west region of the state, Tasmanian Oak's light shades of pale straw to light brown make it a favourite with architects, builders and designers who are looking to inject a modern, crisp feel to their building and design projects.

Tasmanian Oak flooring is machined and dried at Britton's state-of-the-art Tasmanian mill to ensure hard-wearing and high impact resistance which makes it particularly suitable where durability and strength are paramount.

Board Widths

Up to 160mm (wider boards on request)

Covers

12mm Overlay - 65×12, 85×12, 108×12, 133×12

Secret Nailing, End-Matched

65×19, 65×21, 85×19, 108×19, 133×19, 160×19

