

Ridgewood

Australian Wormy Chestnut Flooring

Eucalyptus Obliqua, E.Sieberi and E.Fastigata

Technical Information

Density (kg/m ³ dry)	800	Stability	Good
Specific Gravity	0.8	Sapwood Lyctid Susceptible	No
Modulus of Rupture (MPa dry)	118	Machining	Good
Modulus of Elasticity (GPa dry)	15	Resistance to Split in Nailing	Good
Radial Shrinkage %	3.5	Resistance to Split in Screwing	Good
Tangential Shrinkage %	6	Gluing	Good
Hardness (Janka) (kN)	8	Growing Region	VIC
Finish	Good	Availability	Available

Description

Australian Wormy Chestnut is as individual as you are. The harshness of life deep in Australia's south-eastern forests is etched in to the grainy heart of every Australian Wormy Chestnut floorboard.

Attacks from blistering bushfires, the parched years of drought, the ravages of insects and the sand-blasting of relentless winds shapes a bespoke wood perfect for today's modern design requirements.

Wormy Chestnut is aptly named: squiggly worm trails, ambrosia beetle holes and deep red veins reflect its struggle for survival in the savage beauty of the Australian landscape.

This is a low maintenance wood that makes a statement and is finding favour with designers and architects nationally and internationally.

Sizes

Tongue & Grooved Secret Nailed End Matched
19×85

Tongue & Grooved End Matched

19×130

19×185

Tongue & Grooved Overlay

14×85

14×130

Ridgewood Timber can supply matching stair componentry and stair treads.

