

# Ridgewood

## Blackbutt *Eucalyptus Pilularis*

### Technical Information

Density (kg/m <sup>3</sup> dry)	900	Durable	Yes
Specific Gravity	0.9	Sapwood Lyctid Susceptible	No
Modulus of Rupture (MPa dry)	144	Machining	Good
Modulus of Elasticity (GPa dry)	19	Resistance to Split in Nailing	Good
Radial Shrinkage %	4	Resistance to Split in Screwing	Good
Tangential Shrinkage %	7	Gluing	Poor
Hardness (Janka) (kN)	9	Growing Region	NSW & QLD
Finish	Good	Availability	Widely
Stability	Good		

### Description

Heartwood pale brown, but northern material may sometimes display a slight pinkish tinge. Sapwood distinctively paler.

Texture medium and even. Grain usually straight. Gum veins are common.

#### Suitability

*Boating  
Cabinet Door  
Decking & Cladding  
Flooring & Staircase  
Furniture  
Joinery*

