

Ridgewood

Blue Gum

Eucalyptus Saligna

Technical Information

Density (kg/m ³ dry)	850	Durable	Yes
Specific Gravity	0.85	Sapwood Lyctid Susceptible	Yes
Modulus of Rupture (MPa dry)	140	Machining	Good
Modulus of Elasticity (GPa dry)	18	Resistance to Split in Nailing	Good
Radial Shrinkage %	5	Resistance to Split in Screwing	Good
Tangential Shrinkage %	9	Gluing	Good
Hardness (Janka) (kN)	9	Growing Region	NSW & QLD
Finish	Good		
Stability	Good	Availability	Widely

Description

Heartwood dark pink to red brown. Sapwood usually sufficiently paler to be readily distinguished. Texture moderately coarse and even. Grains straight or slightly interlocked. Gum veins common. *Also known as Sydney Blue Gum.*

Suitability

Boating
Cabinet Door
Decking & Cladding
Flooring & Staircase
Furniture
Joinery