

Ridgewood

## Damar Minyak

*Agathis Dammer, Agathis Borneensis*

### Technical Information

Density (kg/m <sup>3</sup> dry)	550	Durable
Specific Gravity	0.5	Sapwood Lyctid Susceptible
Modulus of Rupture (MPa dry)	67	Machining
Modulus of Elasticity (GPa dry)	12	Resistance to Split in Nailing
Radial Shrinkage %	1.5	Resistance to Split in Screwing
Tangential Shrinkage %	3	Gluing
Hardness (Janka) (kN)	3	Growing Region
Finish	Excellent	
Stability	Good	Availability

### Description

No	Heartwood pale yellowish brown, sometimes with a pinkish tinge. Sapwood often hard to distinguish from the heartwood.
No	
Excellent	Texture very fine and even. Grain straight.
Excellent	No figure. Free of brittleheart.
Excellent	<i>Also known as East Indian Kauri, Indonesian Kauri.</i>
Good	
Asia Pacific	<b>Suitability</b> <i>Boating Cabinet Door Decking &amp; Cladding Flooring &amp; Staircase Furniture Joinery</i>
Widely	