

Ridgewood

## Ironbark Grey

*Eucalyptus Paniculata*

### Technical Information

Density (kg/m <sup>3</sup> dry)	1120
Specific Gravity	1.1
Modulus of Rupture (MPa dry)	181
Modulus of Elasticity (GPa dry)	24
Radial Shrinkage %	4.5
Tangential Shrinkage %	8
Hardness (Janka) (kN)	14
Finish	Fair
Stability	Fair

Durable	Yes
Sapwood Lyctid Susceptible	No
Machining	Fair
Resistance to Split in Nailing	Fair
Resistance to Split in Screwing	Fair
Gluing	Poor
Growing Region	NSW & QLD
Availability	Limited

### Description

Heartwood colour varies from pale brown to dark chocolate brown and also dark red. Texture moderately coarse and even. Grain usually interlocked.

#### Suitability

*Boating*  
*Cabinet Door*  
*Decking & Cladding*  
*Flooring & Staircase*  
*Furniture*  
*Joinery*