

Ridgewood

Ironbark Red

Eucalyptus Sideroxylon

Technical Information

Density (kg/m ³ dry)	1130
Specific Gravity	1.1
Modulus of Rupture (MPa dry)	135
Modulus of Elasticity (GPa dry)	17
Radial Shrinkage %	3.5
Tangential Shrinkage %	7
Hardness (Janka) (kN)	13
Finish	Fair
Stability	Fair

Durable	Yes
Sapwood Lyctid Susceptible	Yes
Machining	Fair
Resistance to Split in Nailing	Fair
Resistance to Split in Screwing	Fair
Gluing	Poor
Growing Region	NSW & QLD
Availability	Limited

Description

Heartwood dark red. Sapwood pale yellow.
Texture medium and even. Grain interlocked.

Suitability

Boating
Cabinet Door
Decking & Cladding
Flooring & Staircase
Furniture
Joinery