

Ridgewood

Jarrah *Eucalyptus Marginata*

Technical Information

Density (kg/m ³ dry)	820	Durable	Yes
Specific Gravity	0.8	Sapwood Lyctid Susceptible	Yes
Modulus of Rupture (MPa dry)	112	Machining	Fair
Modulus of Elasticity (GPa dry)	13	Resistance to Split in Nailing	Fair
Radial Shrinkage %	5	Resistance to Split in Screwing	Fair
Tangential Shrinkage %	8	Gluing	Good
Hardness (Janka) (kN)	8.5	Growing Region	WA
Finish	Good	Availability	Widely
Stability	Good		

Description

Heartwood is a rich dark brownish red, sometimes marked by short, dark brown radial flecks on the end grain and boat shaped flecks on flat sawn surfaces which enhance it's decorative value.

The grain is usually straight but often interlocked or wavy. The texture is even but moderately coarse.

Also known as Western Australian Jarrah.

Suitability

*Boating
Cabinet Door
Decking & Cladding
Flooring & Staircase
Furniture
Joinery*

