

Ridgewood

Marri *Corymbia Calophylla*

Technical Information

Density (kg/m ³ dry)	850	Durable	No
Modulus of Rupture (MPa dry)	125	Sapwood Lyctid Susceptible	Yes
Modulus of Elasticity (GPa dry)	17	Machining	Fair
Radial Shrinkage %	4.5	Resistance to Split in Nailing	Fair
Tangential Shrinkage %	6.6	Resistance to Split in Screwing	Fair
Hardness (Janka) (kN)	7.1	Gluing	Good
Finish	Good	Growing Region	WA
Stability	Good	Availability	Limited

Description

Marri's yellow to pale brown heartwood and paler to white sapwood contrast beautifully with the dark red gum that features on the tree's trunk. It has a coarse but even texture with slightly interlocked grain. The finished timber is honey-coloured with a distinctive vein structure.

Suitability
Furniture
Cabinetmaking
Flooring

