

Ridgewood

Australian Chestnut Flooring

Eucalyptus Obliqua, E.Sieberi and E.Fastigata

Technical Information

Density (kg/m ³ dry)	800	Stability	Good
Specific Gravity	0.8	Sapwood Lyctid Susceptible	No
Modulus of Rupture (MPa dry)	118	Machining	Good
Modulus of Elasticity (GPa dry)	15	Resistance to Split in Nailing	Good
Radial Shrinkage %	3.5	Resistance to Split in Screwing	Good
Tangential Shrinkage %	6	Gluing	Good
Hardness (Janka) (kN)	8	Growing Region	VIC
Finish	Good	Availability	Available

Description

A blend of Australia's most durable and attractive eucalyptus species, the subtle colours and tonal variations of Australian Chestnut Flooring belie its durability and strength.

Tough and hard with a distinctive colour palette, the natural beauty of Australian Chestnut Flooring is proving popular with architects and builders.

Australian Chestnut requires very little maintenance beyond the initial coating and will stand the test of time in a variety of situations.

Sizes

Tongue & Grooved Secret Nailed End Matched
19×85

Tongue & Grooved End Matched
19×130

Tongue & Grooved Overlay
14×85
14×130

Ridgewood Timber can supply matching stair componentry and stair treads.

